

Continental press polished sheets are flame rated and usable for tents, awnings, sunrooms, restaurant patios & enclosures. The standard roll good shrinks 4-8%. With an average shrinkage rate of <1 %, and superior optical clarity without view distortion, Continental press polished sheet is clearly the better choice.

Optically clear versatile awning and recreational enclosure solutions.

- Formulated to meet higher flame standards than standard press polished materials.
- > Minimal shrinkage for a crisp premium fit and finish.
- Unparalleled clarity in your flexible glass provides a beautifully undistorted view at any angle.
- Long-lasting properties keep the view crystal clear for years to come.
- Shrinkage is 4-8% on market roll goods. Continental is less than 1%.



flame protection retardante de llama proteção contra chama FMVSS302/ CA 117E / Cal. Title 19 Section 1237 (small scale)



ductility dúctil ductilidade



light fast and no color change no afecta la luz y sin cambio de color não afeta a luz e sem mudança de cor



easy to clean fácil mantenimiento fácil de limpar



long-lasting *larga vida útil* de longa duração



weather resistant resistencia ante los factores ambientales resistência a fatores ambientais

Continental Options

Tints	clear	
Thickness	20 to 30 mil (050-075 m)	
Dimensions	54 x 110 inches <i>Tolerance +/- 2"</i>	

Property	Results	Method
Luminous Transmittance after Xenon Weathering	> 80% Clear	ASTM DI005
Luminous Transmittance	>95% Retention	ANSI Z26.1, Test 16
Haze	0.5 - 1.0 % <1.0%	ASTM D1003
Tensile Strength	> 3500 PSI	ASTM D412
Tear Resistance	> 550 PSI	ASTM D1004
Low Temperature Impact @ -20° C	No Cracks	SAE J323
Dimensional Stability @100 ° C	<1%	ASTM DI204
Flammability	Seif- Extinguishing	FMVSS 302, CA 117E
Chemical Resistance	Pass	ANSI Z26.1, Test 19 and 20
	 -	Cal title 19 section 1237



Continental A

1944 Valley Avenue | Winchester, Virginia 22601 | USA Phone: 800-894-0426

https://www.continental-industry.com/press-polished-vinyl

The content of this publication is not legally binding and is provided as information only. The trademarks displayed in this publication are the property of Continental AG and/or its affiliates. Copyright © 2020 ContiTech AG. All rights reserved. For complete information go to: www.contitech.de/discl_en