



TRIX® ACETYLENE HOSE - RED

For the safe transport of fuel gases



MARKING: on red cover "Continental TRIX® AUTOGEN 9 x 16 DIN EN ISO 3821 2MPa (20 BAR / 290 PSI) Made in Germany"

APPLICATIONS

Automobile industry, Construction industry, Construction of bridges, Foundries, Garages, Installation and heating system companies, Machinery and plant engineering, Manufacturers of welding apparatus, Over- and underground workings, Shipyards, Steel and iron industry, Steel construction, Welding shops, Workshops

FLOW MEDIUM

Acetylene gas

STANDARD / APPROVAL

DIN
EN ISO
3821:2020

TECHNICAL DATA

nominal width	inner-Ø	wall thickness	outer-Ø	length	working pressure		min. burst pressure		min. bending radius	weight
					bar	psi	bar	psi		
zoll/inch	mm	mm	mm	m	bar	psi	bar	psi	aprx. mm	aprx. g/ m
3/8	9	3,5	16	40	20	290	60	870	90	163
1/2	12,5	4,5	21,5	40	20	290	60	870	125	296
5/8	16	4,5	25	40	20	290	60	870	160	358

Temperature resistance applies only to materials used / All technical data apply at room temperature / High pressure and/or temperature lead to reduced component durability

DESCRIPTION

- Inner lining:** EPDM, black, electrically conductive, $R < 10^6 \Omega/m$, non-porous, smooth
- Reinforcements:** Synthetic fibres
- Cover:** EPDM, black with coated red thin layer, smooth, ozone-resistant
- Working pressure up to:** 20 bar / 290 psi
- Temperature range:** from -20 °C / -4 °F up to +60 °C / +140 °F
- Further properties:** Halogen-free