



# TRIX PAINT SPRAY HOSE EPDM

For simple and safe painting

Ontinental → TRIX® FARBSPRITZ / PAINT SPRAY EPDM DN 9 PN 10 B

**MARKING:** 6 orange, axially applied stripes on a black background "Continental TRIX" FARBSPRITZ / PAINT SPRAY EPDM DN 9 PN 10 BAR / 145 PSI R <  $10^6 \Omega$  Made in Germany"

#### **APPLICATIONS**

Coating companies, Painting companies, Shipyards

#### **FLOW MEDIUM**

Acetone, Ammonia solution - 25%, Caustic soda - 10%, Chlorine rubber lacquer, Dimethyl sulfoxide, Dimethylformamide, Distempers, Emulsion paints, Ester, Ethyl alcohol, Nitro cellulose lacquer, Polyurethane laqcuer, Spirit lacquer, Universal thinner, Water-based paints

## **DESCRIPTION**

**Inner lining:** EPDM, black, non-porous, smooth

**Reinforcements:** Synthetic fibres

**Cover:** EPDM, black, smooth, ozone-resistant

Working pressure up 10 bar / 145 psi

to:

Further properties: Length independently electrically conductive,  $\Omega$ -CL (acc. to EN

ISO 8031)

Temperature range: from +5 °C / +41 °F up to +35 °C / +95 °F

### **TECHNICAL DATA**

nominal width	inner-Ø	wall thickness	outer-Ø	length	working pressure		min. burst pressure		min. bending radius	weight
zoll/inch	mm	mm	mm	m	bar	psi	bar	psi	aprx. mm	aprx. g/ m
3/8	9	3.5	16	40	10	145	40	580	90	230

Temperature resistance applies only to materials used / All technical data apply at room temperature